


**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

**Effective Parameters irrespective of material grade (per set)**

- Effective Length ( $L_e$ ): 49.5mm
- Effective Area ( $A_e$ ): 84.4mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 76.0mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 4178mm<sup>3</sup>


**Approximate weight (without Gap): 22.9g/Set**



## EE2811 Un-gapped (OL)

**Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C**

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)/Set	$P_v$ (W/set)	Ordering code
CF196	2000 $\pm$ 20%	3600 +30%/-20%	$\leq 0.58(200mT, 16kHz, 100^\circ C)$	CF196 EE2811 OL
CF139	2100 $\pm$ 20%	3750 +30%/-20%	$\leq 0.42(100mT, 100kHz, 100^\circ C)$	CF139 EE2811 OL
CF297	2300 $\pm$ 20%	4000 +30%/-20%	$\leq 0.38(100mT, 100kHz, 100^\circ C)$	CF297 EE2811 OL
CF130	3000 $\pm$ 20%	4950 +30%/-20%	$\leq 0.63(200mT, 16kHz, 100^\circ C)$	CF130 EE2811 OL
CF195	5000 $\pm$ 20%	7100 +30%/-20%	-	CF195 EE2811 OL
CF197	7000 $\pm$ 20%	8800 +30%/-20%	-	CF197 EE2811 OL



Remarks: Value of "G" is Zero (0) for Un-Gapped Cores, for Gapped Cores the value of "G" varies as per the Gap/AL value

For general terms and conditions please visit: [http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6\\_GTC.pdf](http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf)